

10/586,471

Preliminary Amendment
Attorney Docket No. 062742

nonmagnetic stainless steel powder in the magnetic layer is in the range of 10% to 40%, the thickness of the magnetic layer is in the range of ~~0.5 to 5.0~~ 1.0 to 4.0 mm, and the ~~woody electric wave absorber~~ electric-wave-absorbing building material has an electric wave absorption characteristic in which the center frequency of the electric waves absorbed lies in the range of 1 to 8 GHz and the amount of electric wave absorption is ~~[[10]]~~ 20 dB or more in a 2.45 GHz frequency band or a 5.2 GHz frequency band.

LC
4/14/09
The present invention also provides (2) the ~~woody electric-wave-absorber~~ electric-wave-absorbing building material according to (1) above, wherein ~~the ferrite powder is composed of Mn-Zn ferrite and~~ the nonmagnetic stainless steel powder is composed of SUS 304 stainless steel.

Please replace the paragraph beginning at page 9, line ~~4~~¹, with the following amended paragraph:

The present invention also provides (3) the ~~woody electric-wave-absorber~~ electric-wave-absorbing building material according to (2) above, wherein the ferrite powder is a ~~mixture in which the ratio by weight represented by Mn-Zn ferrite:Ni-Zn ferrite is in the range of 1:4 to 4:1~~ has a median particle size in the range of 50 to 60 μ m and a particle size range of 45 to 75 μ m.

Please replace the paragraph beginning at page 9, line 16, with the following amended paragraph:

In the ~~electric-wave-absorber~~ electric-wave-absorbing building material of the present invention, as the thickness of the magnetic layer increases, the peak of the maximum amount of